

IBAVINTAGE

Technical Data Sheet

Description

IBAVINTAGE powder coatings are highly decorative finishes consisting of a base colour with a vein pattern of a distinctly different opaque colour.

Characteristics

Aesthetic appearance with wrinkle metallic effect
Applicability in many series and colors
Less waste and pollution to the environment

Applications

Steel doors
Elevator doors
Metal furniture
Sport equipments
Entertainment equipments
Garden tools
Domestic appliances
Decorative applications

Product Properties

Colour	A wide range of wrinkle and vein colours
Surface	Wrinkle WR
Specific gravity	1.5-1.7 gr/cm ³
Shelf Life	12 months (< 30°C and < 50% RH)

Application Data

Application	Check for TDS for the specific series.
Curing	Check for TDS for the specific series.
Film Thickness	80-120µm
Theoretical cons.	5-8 m ² /kg. Practical spreading rates will vary due to such factors as method and conditions of application, specific gravity, surface profile and texture.

IBAVINTAGE

Coating Properties

Test results shown below are based on 0.5 mm steel with 60 μ applied powder coatings.

Direct Impact	>20 kgcm	(ISO 6272-2)
Reverse Impact	>10 kgcm	(ISO 6272-2)
Buchholz Hardness	>90	(ISO 2815)
Conical Mandrel	0 mm	(ISO 6860)
Cross Hatch Adhesion	Gt:0	(ISO 2409)

Application Guide

Surface Preparation

All surfaces should be degreased and pre-treated for optimal performance.

Suitable pre-treatment includes:

Ferrous metals	Zinc phosphate or Iron phosphate
Zinc Coated Metals	Zinc phosphate or chromate

Application Procedure and Equipment

IBAVINTAGE powder coatings charging properties are optimized when powder is free-flowing and moisture-free. Aged or compacted powder may require preconditioning for several minutes to fluidise evenly.

If storage room temperature is lower than the application area, powder coatings, which are hygroscopic, should be acclimated in unopened containers prior to adding into the spray hopper. For optimum performance, It should be applied and stored at air-conditioning area. Storage temperatures should be kept below 30 °C.

Powder should not be stored in hoppers for long periods of time. If moisture condensation occurs, fluidize powder to dry-out or replace moisture-laden powder with virgin powder.

Powder coatings are finely ground particulates. Respirators or dust masks should be used by workers exposed to powder in order to avoid dust inhalation.

Compressed air to the gun must be oil and moisture free.

Silicone should not be used in application area.

For box feeders, ensure probe is fully inserted in powder and operated as per manufacturer's recommendations.

Contact points should be maintained to ensure metal-to-metal ground.

Apply by electrostatic spray. Relative humidity should be 50-60% for corona system, lower than 40% for tribo system.

Cure as per recommendations outlined above.

Reclaim-to-virgin ratios should be carefully monitored to maintain spray consistency.

Sieving powder before adding to hopper eliminates potential clumping or foreign matter.

Test for cure of the coating by impact test.

Read "Application Data" for second layer applications.

Care and Maintenance

IBAVINTAGE powder coatings should be regularly washed with warm water and mild liquid detergent, followed by a fresh water rinse to maintain the attractive appearance of the powder cured film. The use of abrasive cleaners is not recommended, nor is the use of active organic solvents.

Health and Safety

The SDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed. It is recommended to contact to Sales and Customer Service Offices for further information.

IBAVINTAGE

Precautions and Limitations

As a result of possible wide application variations and stoving conditions, **IBAVINTAGE** powder coatings may show variation, between İBA Kimya Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.

For optimum performance ensures recommended dry film thickness is obtained.

The metallic effect of the cured powder coating will vary when the same powder coating is applied through different spray equipment.

Transport and Storage

Packaging

15-20 kgs. Heavy polyethylene bag in a corrugated carton

Shipment

Not dangerous goods. No special transport requirements.

Storage Conditions

Storage temperatures should be kept below 30 C° and 50% relative humidity. Powder should be stored in closed containers.



DISCLAIMER: All the information given in this Data Sheet is the result of our research work experience. It is given in good faith and with every belief in its accuracy but cannot be considered as a formal warranty. In accordance with İBA KİMYA, policy of product development, this specification is subject to change without notice.