

IBAMIX

Technical Data Sheet

Description

IBAMIX powder coatings are decorative looking products obtained by physically mixing different coloured powder coatings. **IBAMIX** powder coatings are available in all chemistry, like epoxy-polyester, polyester TGIC and TGIC-free versions.

Characteristics

Aesthetic appearance with mixed effect
Improved application characteristics
Less waste and pollution to the environment

Applications

Metal furniture
Lighting equipment
Electronic equipment
Steel doors
White goods
Shelving systems
Architectural applications
Decorative applications

Product Properties

Colour	A wide range of mixed colours
Surface	Gloss GL – Semigloss HR – Semimatt CS – Matt CM – Structure ST – Wrinkle WR
Specific gravity	Check for TDS for the specific series.
Shelf Life	Check for TDS for the specific series.

Application Data

Application	Corona/Tribo (Can be applied by tribo guns if product code has "T" for the 6th character)
Curing	Check for TDS for the specific series.
Film Thickness	Check for TDS for the specific series.
Theoretical cons.	Check for TDS for the specific series.

Application Guide

IBAMIX powder coating does not require a special application. Check TDS for the specific series.

IBAMIX

Care and Maintenance

IBAMIX powder coatings should be regularly washed with warm water and mild liquid detergent, followed by a fresh water rinse to maintain the attractive appearance of the powder cured film. Use a soft cloth that does not scratch the surface. The detergent used for non-chemical resistant products should have a neutral pH. The surface should not be left with detergent for a long time and should be rinsed immediately with water.

The use of abrasive cleaners is not recommended, nor is the use of active organic solvents.

Health and Safety

The SDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed. It is recommended to contact to Sales and Customer Service Offices for further information.

Precautions and Limitations

As a result of possible wide application variations and stoving conditions, **IBAMIX** powder coatings may show variation, between İBA Kimya Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.

For optimum performance ensures recommended dry film thickness is obtained.

IBAMIX powder coatings should be homogeneous before application. To ensure this, the entire box must be placed in the feeding chamber and should be fluidized for about 10 minutes at minimum level which will provide gurgitation in the chamber.

The mixed effect of the cured powder coating will vary when the same powder coating is applied through different spray equipment.

The mixed effect may change when using recycled coating. If recycled coating is used, it should be added homogeneously.

Transport and Storage

Packaging	15-20 kgs. Heavy polyethylene bag in a corrugated carton
Shipment	Not dangerous goods. No special transport requirements.
Storage Conditions	Storage temperatures should be kept below 30 C° and 50% relative humidity. Powder should be stored in closed containers.

IBAMIX



DISCLAIMER: All the information given in this Data Sheet is the result of our research work experience. It is given in good faith and with every belief in its accuracy but cannot be considered as a formal warranty. In accordance with İBA KİMYA, policy of product development, this specification is subject to change without notice.