

## IBASHIELD – ZINC RICH

# Technical Data Sheet

### Description

**IBASHIELD - Zinc Rich** primer powder coatings are zinc rich epoxy based thermosetting sacrificial powder coatings designed to enhance the corrosion resistance of steel items. Sacrificial coatings contain certain elements, such as zinc, which oxidize sacrificially to ensure that the substrate remains corrosion free. Sacrificial coatings essentially fool the rust into eating away at the coating instead of the metal layers beneath.

**IBASHIELD - Zinc Rich** primer powder coatings have been designed as an undercoat for powder topcoats such as PE55, PE58, PS70, PS77... or any other topcoat and for more corrosive environments as an undercoat for other base coats.

**Series:** EE20AC7776898GLX and EE20AC7777198GLX Zinc Primer

**NOTE:** EE20AC7776898GLX has lower zinc content. It can be preferred for applications where lower corrosion resistance is sufficient with lower cost.

### Characteristics

**Series:** EE20AC7776898GLX and EE20AC7777198GLX Zinc Primer

Excellent corrosion resistance

Increasing service life

No solvents or emissions

Less waste and pollution to the environment

Good chemical resistance

Excellent corrosion protection

### Applications

Gas cylinders and tanks

Agricultural machinery

Street and garden furniture

Valves

**IBASHIELD - Zinc Rich** primer powder coatings have a multitude of uses over a steel objects. If chemical treatment is difficult, a zinc-rich powder primer provides the solution on shot blasted steel.

### Product Properties

**UV Resistance** Not recommended for exterior use. It contains an epoxy component which will chalk on exterior exposure. Can be used for exterior applications, if any outdoor durable topcoat is applied.

**Color** Zinc Grey

**Surface** Gloss GL


**Specific gravity** 2.0-2.2 gr/cm<sup>3</sup>

**Shelf Life** 6 months (< 30°C and < 50% RH)

## IBASHIELD – ZINC RICH

### Application Data

<b>Application</b>	Corona (Can be applied by tribo guns if product code has "T" for the 6th character)	
<b>Curing</b>	190°C 10 minutes recommended	
	<b>Metal Temperature (°C)</b>	<b>Time (minutes)</b>
	180	15-25
	190	8-18
	200	6-14



**Film Thickness** 40-50µ (recommended)

**Theoretical cons.** 0-12 m<sup>2</sup>/kg. Practical spreading rates will vary due to such factors as method and conditions of application, specific gravity, surface profile and texture.

### Coating Properties

Test results shown below are based on 0.5 mm steel with 60µ applied powder coatings.

<b>Direct Impact</b>	>5 kgcm	(ISO 6272-2)
<b>Reverse Impact</b>	>5 kgcm	(ISO 6272-2)
<b>Buchholz Hardness</b>	>90	(ISO 2815)
<b>Conical Mandrel</b>	<5 mm	(ISO 6860)
<b>Cross Hatch Adhesion</b>	Gt:0	(ISO 2409)

### Application Guide

#### Surface Preparation

All surfaces should be degreased and pre-treated for optimal performance.

Application recommendations due to corrosivity categories are given in "Product Specification Sheet" for **IBASHIELD - Zinc Rich** primer powder coatings.

#### Application Procedure and Equipment

**IBASHIELD - Zinc Rich** primer powder coatings charging properties are optimized when powder is free-flowing and moisture-free. Aged or compacted powder may require preconditioning for several minutes to fluidise evenly.

If storage room temperature is lower than the application area, powder coatings, which are hygroscopic, should be acclimated in unopened containers prior to adding into the spray hopper. For optimum performance, It should be applied and stored at air-conditioning area. Storage temperatures should be kept below 30°C.

Powder should not be stored in hoppers for long periods of time. If moisture condensation occurs, fluidize powder to dry-out or replace moisture-laden powder with virgin powder.

Powder coatings are finely ground particulates. Respirators or dust masks should be used by workers exposed to powder in order to avoid dust inhalation.

Compressed air to the gun must be oil and moisture free.

Silicone should not be used in application area.

For box feeders, ensure probe is fully inserted in powder and operated as per manufacturer's recommendations.

**IBASHIELD - Zinc Rich** primer powder coatings have a higher than average specific gravity, box feeders will need to be tested to make sure an adequate transfer of powder can be achieved.

Contact points should be maintained to ensure metal-to-metal ground.

Apply by electrostatic spray. Relative humidity should be 50-60% for corona system, lower than 40% for tribo system.

It is recommended that **IBASHIELD - Zinc Rich** primer powder coatings be top coated within 12 hours due to a possible moisture uptake of the coating.

## IBASHIELD – ZINC RICH

If top coat applied within 12 hours. Partially cure for 3 - 5 minutes at 190°C metal temperature. Use top coat cure schedule to complete cure of **IBASHIELD - Zinc Rich** primer powder coatings.

If top coat applied after 12 hours. Full cure for 10 minutes at 190°C metal temperature. Avoid over cure as this will inhibit intercoat adhesion with top coat. Store in clean, dry environment until the next stage the condition of storage between coats has direct effect on adhesion.

If no top coat to be applied. Full cure for 10 minutes at 190°C metal temperature.

Reclaim-to-virgin ratios should be carefully monitored to maintain spray consistency.

Sieving powder before adding to hopper eliminates potential clumping or foreign matter.

### Atmospheric Corrosivity Categories and Examples of Typical Environments (BS EN ISO 12944-2)

Environments causing corrosion can be classified in different categories according to their corrosivity.

Corrosivity Category and Risk	Examples of typical environments in a temperate climate (informative only)	
	Exterior	Interior
<b>C1</b> very low	-	Heated buildings with clean atmospheres, e.g. offices, shops, schools, hotels
<b>C2</b> low	Atmospheres with low level of pollution Mostly rural areas	Unheated buildings where condensation may occur, e.g. depots, sports halls
<b>C3</b> medium	Urban and industrial atmospheres, moderate sulphur dioxide pollution Coastal area with low salinity	Production rooms with high humidity and some air pollution e.g. food-processing plants, laundries, breweries, dairies
<b>C4</b> high	Industrial areas and coastal areas with moderate salinity	Chemical plants, swimming pools, coastal, ship and boatyards
<b>C5-I</b> very high (industrial)	Industrial areas with high humidity and aggressive atmosphere	Buildings or areas with almost permanent condensation and high pollution
<b>C5-M</b> very high (marine)	Coastal and offshore areas with high salinity	Buildings or areas with almost permanent condensation and high pollution

### Zinc Free IbaShield Selection Guide

**Notes:**

- (1) For C5-I and C5-M environments, we kindly request to consult İba Kimya for specially formulated products for specific demands.
- (2) Coating should be applied on abrasive blasted steel immediately to prevent oxidation.
- (3) For C3, C4, C5-I and C5-M environments, for İba Kimya "X" and "B" coded metallic effect top coats, İba Kimya Clear coats are recommended as final top coat.

## IBASHIELD – ZINC RICH

Corrosivity Category	Protection Time	Examples of environments	Salt Spray Test	Pretreatment + IBASHIELD – Zinc Rich
C2, low		Rural areas with low pollution		-
C3, medium	2-5 years 5-15 yrs > 15 yrs	Moderately polluted urban / industrial areas	120 hrs 240 hrs 480 hrs	Sandblasting Sandblasting+7776 Sandblasting+7776
C4, high	2-5 yrs 5-15 yrs > 15 yrs	Industry, tunnel, traffic ports	240 hrs 480 hrs 720 hrs	Sandblasting+7776 Sandblasting+7776 Sandblasting+7777
C5-I very high (industrial)	2-5 yrs 5-15 yrs > 15 yrs	Industrial areas with high humidity and aggressive atmosphere	480 hrs 720 hrs 1440 hrs	Sandblasting+7776 Sandblasting+7777 Sandblasting+7777+EE20
C5-M very high (marine)	2-5 yrs 5-15 yrs > 15 yrs	Coastal areas with high salinity	480 hrs 720 hrs 1440 hrs	Sandblasting+7776 Sandblasting+7777 Sandblasting+7777+EE20

### Care and Maintenance

**IBASHIELD - Zinc Rich** primer powder coatings are hard wearing coatings, most often used in areas where aesthetics are not important. Unlike common decorative coatings, no formal cleaning program is required. However it is better to remove salts and other pollutant deposits where possible, and repair any exposed metal surfaces with appropriate repair kit.

### Health and Safety

The SDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed. It is recommended to contact to Sales and Customer Service Offices for further information.

Powder-in-air concentrations of greater than 20 gr/m<sup>3</sup> to 70 gr/m<sup>3</sup> can be ignited by flame or strong electrical discharge. Powder concentrations below 20 gr/m<sup>3</sup> or above 70 gr/m<sup>3</sup> are too sparse or too dense to support flame or combustion. Properly engineered application equipment is designed to keep powder-in-air concentrations well below this range. All equipment should be inspected periodically for proper operation and electrical ground. Hangers, hooks, racking system, and conveyor should be cleaned to eliminate powder build-up. Eliminate all sources of ignition.

### Precautions and Limitations

As a result of possible wide application variations and stoving conditions, **IBASHIELD - Zinc Rich** primer powder coatings may show variation, between İBA Kimya Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.

For optimum corrosion performance ensures recommended dry film thickness is obtained.

Not recommended for exterior applications. (unless an outdoor topcoat is applied)

Over baking may result in intercoat adhesion problems. For optimal intercoat adhesion refer the cure details in the "application guide" section of this data sheet.

## IBASHIELD – ZINC RICH

### Transport and Storage

<b>Packaging</b>	25 kgs. Heavy polyethylene bag in a corrugated carton
<b>Flashpoint</b>	Powder-in-air concentrations of greater than 20 gr/m <sup>3</sup> to 70 gr/m <sup>3</sup>
<b>Shipment</b>	Not dangerous goods. No special transport requirements.
<b>Storage Conditions</b>	Storage temperatures should be kept below 30 C° and 50% relative humidity. Powder should be stored in closed containers.

*DISCLAIMER: All the information given in this Data Sheet is the result of our research work experience. It is given in good faith and with every belief in its accuracy but cannot be considered as a formal warranty. In accordance with İBA KİMYA, policy of product development, this specification is subject to change without notice.*