

## IBAGRAFF\_PU40

# Technical Data Sheet

### Description

**IBAGRAFF\_PU40** is an exterior durable thermosetting powder coating based on polyurethane resins designed for anti-graffiti and whiteboard applications. It features excellent chemical resistance and superior weather resistance. It can be used to produce surface finishes which are nearly resistant to all types of graffiti. Sprayed paint can be removed without a trace.

### Characteristics

Excellent chemical resistance  
Resists solvents and detergents  
Easy to remove most forms of graffiti  
Suitable for most environments  
Available for all colors  
Less waste and pollution to the environment  
High resistance to weather and corrosion

### Applications

Vehicles for public transport  
Outdoor furniture  
Bus shelters  
Telephone boxes  
Noise-protection walls  
Toilet and shower cubicles  
Furniture for schools


### Product Properties

<b>UV Resistance</b>	Good UV resistance.
<b>Flow out</b>	Good
<b>Surface</b>	Gloss GL – Semigloss HR – Semimatt CS
<b>Specific gravity</b>	1.5-1.8 gr/cm <sup>3</sup> (low with dark colours, high with light colours)
<b>Shelf Life</b>	12 months (< 30°C and < 50% RH)

# IBAGRAFF\_PU40

## Application Data

<b>Application</b>	Corona (Can be applied by tribo guns if product code has "T" for the 6th character)
<b>Curing</b>	190°C 10 minutes recommended
	Metal Temperature (°C)      Time (minutes)
	180                                  15-25
	190                                  8-18
	200                                  6-14



**Film Thickness** 60-80 µm (recommended)\*

**Theoretical cons.** 8-10 m<sup>2</sup>/kg. Practical spreading rates will vary due to such factors as method and conditions of application, specific gravity, surface profile and texture.

*\*Recommended film thickness for WR coded products is 80-130µ, theoretical consumption value should be calculated due to this thickness range.*

## Coating Properties

Test results shown below are based on 0.5 mm steel with 60µ applied powder coatings.

<b>Direct Impact</b>	>20 kgcm	(ISO 6272-2)
<b>Reverse Impact</b>	>20 kgcm	(ISO 6272-2)
<b>Buchholz Hardness</b>	>90	(ISO 2815)
<b>Conical Mandrel</b>	0 mm	(ISO 6860)
<b>Cross Hatch Adhesion</b>	Gt:0	(ISO 2409)
<b>NSS 1000hrs</b>	Excellent (0.8mm chromated aluminium)	(ISO 9227)
<b>Chemical Resistance</b>	Methyl Ethyl Ketone MEK	resistant
	Ethanol	resistant
	Methyl Isobutyl Ketone MIBK	resistant
	White Spirits	resistant
	Ethyl Acetate	resistant
	10% Acetic Acid	resistant
	10% Hydrochloric Acid	resistant
	10% Ammonium Hydroxide	resistant

*\* Mechanical properties may decrease for WR coded products due to higher film thickness values.*

## Application Guide

### Surface Preparation

All surfaces should be degreased and pretreated for optimal performance.

Suitable pretreatment includes:

Aluminium	Yellow chromate or green chromate/phosphate
Ferrous metals	Zinc phosphate or Iron phosphate
Zinc Coated Metals	Zinc phosphate or chromate

## IBAGRAFF\_PU40

### Application Procedure and Equipment

**IBAGRAFF\_PU40** series powder coatings charging properties are optimized when powder is free-flowing and moisture-free. Aged or compacted powder may require preconditioning for several minutes to fluidise evenly.

If storage room temperature is lower than the application area, powder coatings, which are hygroscopic, should be acclimated in unopened containers prior to adding into the spray hopper. For optimum performance, it should be applied and stored at air-conditioning area. Storage temperatures should be kept below 30 °C.

Powder should not be stored in hoppers for long periods of time. If moisture condensation occurs, fluidize powder to dry-out or replace moisture-laden powder with virgin powder.

Powder coatings are finely ground particulates. Respirators or dust masks should be used by workers exposed to powder in order to avoid dust inhalation.

Compressed air to the gun must be oil and moisture free.

Silicone should not be used in application area.

For box feeders, ensure probe is fully inserted in powder and operated as per manufacturer's recommendations.

Contact points should be maintained to ensure metal-to-metal ground.

Apply by electrostatic spray. Relative humidity should be 50-60% for corona system, lower than 40% for tribo system.

Cure as per recommendations outlined above.

Reclaim-to-virgin ratios should be carefully monitored to maintain spray consistency.

Sieving powder before adding to hopper eliminates potential clumping or foreign matter.

Test for cure of the coating by impact test.

### Care and Maintenance

**IBAGRAFF\_PU40** should be regularly washed with warm water and mild liquid detergent, followed by a fresh water rinse to maintain the attractive appearance of the powder cured film.

Graffiti on PU40 can be removed by cleaning with Methylated Spirits (denatured alcohol) or Methyl Isobutyl Ketone MIBK. Other solvents can be used but should be tested on a small area first. 30 second wipe with the recommended Graffiti removers. Always rinse after cleaning with fresh water to remove any remaining solvent.

The use of abrasive cleaners is not recommended, nor is the use of active organic solvents.

### Health and Safety

The SDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed. It is recommended to contact to Sales and Customer Service Offices for further information.

### Precautions and Limitations

As a result of possible wide application variations and stoving conditions, **IBAGRAFF\_PU40** may show variation, between İBA Kimya Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.

For optimum corrosion performance ensures recommended dry film thickness is obtained.

Not recommended for use in highly corrosive environments.

It is best to clean graffiti as soon as possible so the paint doesn't have time to absorb into the surface.

## IBAGRAFF\_PU40

### Transport and Storage

<b>Packaging</b>	15-20 kgs. Heavy polyethylene bag in a corrugated carton
<b>Shipment</b>	Not dangerous goods. No special transport requirements.
<b>Storage Conditions</b>	Storage temperatures should be kept below 30 C° and 50% relative humidity. Powder should be stored in closed containers

*DISCLAIMER: All the information provided in this data sheet depends on our knowledge and experience up to date and may be subject to revision as new technology and experience evolve. Since the conditions of application may vary depending on the substrate, physical conditions and other variables, users should conduct necessary tests to determine the conformity of the product for its intended use. We do not accept liability since the application, use and processing of the products take place beyond our control and supervision. Moreover, our liability for breach of warranty is exclusively limited to replacement of the product or refund of its price and we are not liable for incidental, indirect or consequential damages under any circumstances.*