

## IBAHEAT – EE56

# Technical Data Sheet

### Description

IBAHEAT – EE56 is a thermosetting powder coating based on acrylic silicone resins providing after complete curing, a film with high thermic resistance. IBAHEAT – EE56 will resist to continuous exposure to temperatures as high as 330°C. IBAHEAT – EE56 series can be produced with FDA approval upon request.

### Characteristics

Black and metallic grey colours  
Less waste and pollution to the environment  
Suitable for most indoor environments  
Service temperature 330°C for long exposures and peak temperature 350°C.  
One coat finishes  
Very good mar resistance  
Pencil hardness is 3H when it is properly cured  
Anti-adherent properties for oils and fats  
Oils and fats can easily be removed with water and current housekeeping detergents  
FDA approved upon request

### Applications

External coatings of cooking utensils  
Barbecue sets and accessories  
Coating of heat devices  
Protective coating of electrical appliances operating at elevated temperatures

### Product Properties

<b>UV Resistance</b>	Good UV resistance.
<b>Flow out</b>	Medium
<b>Surface</b>	Semigloss HR – Semimatt CS – Matt CS – Structure ST
<b>Specific gravity</b>	1.7-1.9 gr/cm <sup>3</sup>
<b>Shelf Life</b>	12 months (< 30°C and < 50% RH)

### Application Data

<b>Application</b>	Corona (Can be applied by tribo guns if product code has "T" for the 6th character)
<b>Curing</b>	210°C 10 minutes recommended
<b>Film Thickness</b>	50-60µ (recommended)
<b>Theoretical cons.</b>	8-10 m <sup>2</sup> /kg. Practical spreading rates will vary due to such factors as method and conditions of application, specific gravity, surface profile and texture.

## IBAHEAT – EE56

### Coating Properties

Test results shown below are based on 0.5 mm steel with 60µ applied powder coatings.

<b>Direct Impact</b>	>20 kgcm	(ISO 6272-2)
<b>Reverse Impact</b>	>10 kgcm	(ISO 6272-2)
<b>Buchholz Hardness</b>	>100	(ISO 2815)
<b>Conical Mandrel</b>	< 20 mm	(ISO 6860)
<b>Cross Hatch Adhesion</b>	Gt:0	(ISO 2409)

### Application Guide

#### Surface Preparation

All surfaces should be degreased and pretreated for optimal performance.

**IBAHEAT – EE56** series is preferably applied onto slightly shot blasted metals.

for steel : fine steel shot or grit

for aluminium, zinc other non-ferrous metal : corundum

**WARNING !** because of the high service temperature reached by **IBAHEAT – EE56**, it is not advised to apply any type of chemical pretreatment.

#### Application Procedure and Equipment

**IBAHEAT – EE56** series powder coatings charging properties are optimized when powder is free-flowing and moisture-free. Aged or compacted powder may require preconditioning for several minutes to fluidise evenly.

If storage room temperature is lower than the application area, powder coatings, which are hygroscopic, should be acclimated in unopened containers prior to adding into the spray hopper. For optimum performance, It should be applied and stored at air-conditioning area. Storage temperatures should be kept below 30°C.

Powder should not be stored in hoppers for long periods of time. If moisture condensation occurs, fluidize powder to dry-out or replace moisture-laden powder with virgin powder.

Powder coatings are finely ground particulates. Respirators or dust masks should be used by workers exposed to powder in order to avoid dust inhalation.

Compressed air to the gun must be oil and moisture free.

Silicone should not be used in application area.

For box feeders, ensure probe is fully inserted in powder and operated as per manufacturer's recommendations.

Contact points should be maintained to ensure metal-to-metal ground.

Apply by electrostatic spray. Relative humidity should be 50-60% for corona system, lower than 40% for tribo system.

Cure as per recommendations outlined above.

Reclaim-to-virgin ratios should be carefully monitored to maintain spray consistency.

Sieving powder before adding to hopper eliminates potential clumping or foreign matter.

Test for cure of the coating by impact test.

### Care and Maintenance

**IBAHEAT – EE56** should be regularly washed with warm water and mild liquid detergent, followed by a fresh water rinse to maintain the attractive appearance of the powder cured film.

The use of abrasive cleaners is not recommended, nor is the use of active organic solvents.

## IBAHEAT – EE56

### Health and Safety

The SDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed. It is recommended to contact to Sales and Customer Service Offices for further information.

### Precautions and Limitations

The temperature resistance of the **IBAHEAT – EE56** series may vary depending on the application conditions, such as the heating rate of the material and the ambient conditions in the application, it must be checked by making tests in the end use system. As a result of possible wide application variations and stoving conditions, **IBAHEAT – EE56** may show variation, between İBA Kimya Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.

For optimum corrosion performance ensures recommended dry film thickness is obtained.

Not recommended for exterior applications.

The powder film gets softening at high temperature (~300°C). Do not contact with hard materials at high temperatures.

**IBAHEAT – EE56** is not suitable for direct contact with open flame.

### Transport and Storage

<b>Packaging</b>	15-20-25 kgs. Heavy polyethylene bag in a corrugated carton
<b>Shipment</b>	Not dangerous goods. No special transport requirements.
<b>Storage Conditions</b>	Storage temperatures should be kept below 30 C° and 50% relative humidity. Powder should be stored in closed containers.

*DISCLAIMER: All the information provided in this data sheet depends on our knowledge and experience up to date and may be subject to revision as new technology and experience evolve. Since the conditions of application may vary depending on the substrate, physical conditions and other variables, users should conduct necessary tests to determine the conformity of the product for its intended use. We do not accept liability since the application, use and processing of the products take place beyond our control and supervision. Moreover, our liability for breach of warranty is exclusively limited to replacement of the product or refund of its price and we are not liable for incidental, indirect or consequential damages under any circumstances.*