

iBA KiMYA SAN. ve TiC. A.Ş.

1. Organize Sanayi Bölgesi
Oğuz Caddesi No:22
06930 Sincan / Ankara / Türkiye
Tel:+90312 267 09 83 Fax:+90312 267 09 87
www.iba.com.tr

PRIMOSTAT

Ürün Teknik Bilgisi

Description

PRIMOSTAT is a special solution which is developed for powder coating applications where adhesion is difficult for non-conductive surfaces such as glass, plastic or ceramics. This product increases the electrical conductibility of the surface.

Product Properties

Solution specific gravity

 $0.8 - 0.9 \,\mathrm{gr/cm}^3$

Application Guide

Application Method

PRIMOSTAT can be prepared by slowly adding water and diluting to 1/10 ratio. Although the properties remain constant for weeks, it's recommended to prepare fresh solution before use.

Surface should be cleaned from oil, dirt and dust. Then, **PRIMOSTAT** solution an be applied either by spraying or by immersion techniques. The final coat of powder paint application must be made within a maximum of 2 hours.

Precautions and Limitations

PRIMOSTAT is neither flammable nor toxic.

Good ventilation is required during application and drying.

DISCLAIMER: All the information provided in this data sheet depends on our knowledge and experience up to date and may be subject to revision as new technology and experience evolve. Since the conditions of application may vary depending on the substrate, physical conditions and other variables, users should conduct necessary tests to determine the conformity of the product for its intended use. We do not accept liability since the application, use and processing of the products take place beyond our control and supervision. Moreover, our liability for breach of warranty is exclusively limited to replacement of the product or refund of its price and we are not liable for incidental, indirect or consequential damages under any circumstances.'